

Processing Data

Grade PC200

20 melt superior processing, fast cycling

Injection Molding Parameters	Nominal Values (English)
Drying Temperature	250 °F
Drying Time	3-4 Hours
Drying Time, Maximum	48 Hours
Melt Temperature	520-560 °F
Nozzle Temperature	510-550 °F
Front Temperature	520-560 °F
Middle Temperature	500-540 °F
Rear Temperature	480-520 °F
Mold Temperature	160-200 °F
Back Pressure	50-100 psi
Screw Speed	40-70 rpm
Suggested Shot Size	40-60 %
Vent Depth	.001-.003 in

The values shown are typical values that have been obtained using test bars molded from laboratory samples and are not intended for specification purposes. These values are for natural colors only. Addition of pigments may alter some values. Inasmuch as LTL Color Compounders has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own test to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any LTL Color Compounders patent covering such use or as recommendations for use of such materials in the infringement of any patent. These are developmental products with estimated physical property profiles. Actual values will need to be determined upon production of material.