

Product Data Sheet

Grade NY2115

8/5/2003

Super tough nylon 6,6 with excellent chemical resistance and ductility

Properties

PHYSICAL	Test Method	Typical Values, Units
Specific Gravity	ASTM D792	1.05 g/cm ³
Melt Flow Rate (276 C/5000g)	ASTM D1238	30 g/10 min
Mold Shrinkage Linear Flow (0.125)	ASTM D955	0.15 to 0.20 in/in
Water Absorption @ 24 hrs	ASTM D570	1.3 %
IMPACT	Test Method	Typical Values, Units
Izod Impact Strength Notched (73 F)	ASTM D256	16 ft-lb/in
MECHANICAL	Test Method	Typical Values, Units
Tensile Strength @ Yield**	ASTM D638	7600 psi
Tensile Strength @ Break**	ASTM D638	6800 psi
Elongation @ Yield*	ASTM D638	18 %
Elongation @ Break*	ASTM D638	70 %
Flexural Strength***	ASTM D790	10500 psi
Flexural Modulus***	ASTM D790	290000 psi
HARDNESS	Test Method	Typical Values, Units
Hardness (D-scale)	ASTM D785	75
THERMAL	Test Method	Typical Values, Units
DTUL @ 264 psi Unannealed (.250)	ASTM D648	160 °F
IGNITION CHARACTERISTICS	Test Method	Typical Values, Units
UL File Number Flame Rating - UL		

* % elongation values are calculated from the elongation of the entire bar at 2.0 in/min

** Tensile strength values are calculated at 2.0 in/min

*** Flexural data is calculated at 2.0 in/min

The values shown are typical values that have been obtained using test bars molded from laboratory samples and are not intended for specification purposes. These values are for natural colors only. Addition of pigments may alter some values. Inasmuch as LTL Color Compounders has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own test to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any LTL Color Compounders patent covering such use or as recommendations for use of such materials in the infringement of any patent. These are developmental products with estimated physical property profiles. Actual values will need to be determined upon production of material.